

SPF12V200-ST STANDARD TYPE BATTERY

ELECTRICAL PERFORMANCE			
Nominal Voltage	12.8 V		
Nominal Capacity	200Ah		
Capacity @ 40A	300 min		
Energy	2560Wh		
Resistance	≤12mΩ @ 50% SOC		
Self Discharge	<3% / Month		
Cells	Cylindrical		



CHARGE PERFORMANCE			
Recommended Charge Current	40A		
Maximum Charge Current	100A		
Recommended Charge Voltage	14.6V		
BMS Charge Cut-Off Voltage	<15V (3.75V/Cell)		
Reconnect Voltage	>14.2V(3.55V/Cell)		
Balancing Voltage	<14.4V (3.6V/Cell)		
Maximum Batteries in Series	4		

DISCHARGE PERFORMANCE			
Maximum Continuous Discharge Current	ischarge Current 150A		
Peak Discharge Current	300A (3s)		
BMS Discharge Cut-Off Current	450A ± 20A (31 ms)		
Recommended Low Voltage Disconnect	11.0V (2.75V/Cell)		
BMS Discharge Cut-Off Voltage	>9.2V (1s) (2.3V/Cell)		
Reconnect Voltage	>10.8V(2.7V/Cell)		
Short Circuit Protection	250 ~ 500 µs		


MECHANICAL PERFORMANCE		
Dimension (L x W x H)	484x 170 x 241mm 19.0 x 6.7x9.5"	
Approx. Weight	55.4 lbs (25.2 kg)	
Terminal Type	T11	
Terminal Torque	80 - 100 in-lbs (9 - 11 N-m)	
Case Material	ABS	
Enclosure Protection	IP65	


TEMPERATURE PERFORMANCE			
Discharge Temperature	-4 ~ 140°F (-20 ~ 60 °C)		
Charge Temperature	32 ~ 113 °F (0 ~ 45 °C)		
Storage Temperature	23 ~ 95 °F (-5 ~ 35 °C)		
BMS High Temperature Cut-Off	167 °F (75 °C)		
Reconnect Temperature	149 °F (65 °C)		

COMPLIANCE	
Certification	CE (battery) UN38.3 (battery) UL1642 & IEC62133 (cells)
Shipping Classification	UN 3480, CLASS 9

OUTLINE DIMENSION









L mm(")	W mm(")	H mm(")	HT mm(")
484 (19)	170 (6.7)	218(8.6)	241 (9.5)






PERFORMANCE CHARACTERISTICS






FEATURES & BENEFITS



Discharge characteristic at different rate at room temperature



Lithium Iron Phosphate can be used in most applications that use Lead Acid, GEL or AGM type batteries.

Suitable applications include:

- Marine
- Caravan
- Golf car
- Buggies
- Solar Storage
- Remote Monitoring
- · Switching applications and more

CAUTIONS

- Do NOT short circuit, reverse polarity, crush or disassemble.
- Do NOT heat or incinerate.
- Do NOT immerse in any liquid.
- Store at 30~50% SOC. Recharging every 3 months is recommended. The storage area should be clean, cool, dry and ventilated

Performance may vary depending on application. All specifications are subject to change without prior notice to the user. This data is for evaluation purposes only. No guarantee is intended or implied by this data.



Longer service life

of ownership

High cycle life

Low maintenance batteries with stable chemistry.

>2000 cycles @80% DoD for effectively lower total cost

BMS

Built in circuit protection

Battery Management System (BMS) is incorporated against abuse.

Better storage

up to 6 months thanks to its extremely low self discharge (LSD) rate and no risk of sulphation

Quickly recharge

Save time and increase productivity with less down time thanks to superior charge/discharge efficiency.



 \bigcirc

Extreme heat tolerance Suitable for use in a wider range of applications where

ambient temperature is unusually high: up to +60°C.

Light weight

Lithium batteries provide more Wh/Kg while also being up to 1/3 the weight of its SLA equivalent.

